



Kaiheng Graphite Carbon

Regular Power Graphite Electrode Specifications

Properties	Units	Values	
Bulk Density	g/cm ³	Electrode	≅ 1.58
		Nipple	≅ 1.65
Electrical Resistivity	μΩm	Electrode	≅ 8.5
		Nipple	≅ 5.0
Flexible Strength	MPa	Electrode	≅ 12.0
		Nipple	≅ 16.0
Elastic Modulus	GPa	Electrode	≅ 8.0
		Nipple	≅ 12.0
Coefficient of Thermal Expansion (100°C-600°C)	10 ⁻⁶ /°C	Electrode	≅ 2.9
		Nipple	≅ 2.9
Ash	%	-	≅ 0.3

Length: 1000mm-2700mm.

Diameter: 75mm-450mm.

ADD: 919, Jin'ao International Building, Maidian East Road, Haidian District, Beijing 100088, China.

TEL: +86-15601234979

FAX: +86-10-82207122

EMAIL: sales@kh-graphite-carbon.com

WEB: www.kh-graphite-carbon.com