



Kaiheng Graphite Carbon

Extrusion Moulding Graphite Rods & Blocks Specifications (II)

Parameters	Units	Values						
Bulk Density	g/cm ³	1.65	1.68	1.70	1.76	1.80	1.82	1.85
Porosity	%	24	20	20	20	16	16	16
Specific Resistance	μΩm	16	15	18	15	14	14	14
Compressive Strength	MPa	42	50	50	50	65	70	70
Flexible Strength	MPa	20	22	22	20	30	35	35
Ash	%	0.08	0.08	0.02	0.001-0.02	0.01	0.01	0.01
Dimensions	mm	Φ55*120	Φ60*120	Φ130*200	Φ130*250			Φ133*250
		Φ95*120	Φ70*120	Φ140*200	Φ140*250	Φ140*250	300*200*160	300*200*160
		Φ110*120	207*148*120	Φ150*200	Φ150*250	Φ150*250	400*300*400	400*300*400
			250*168*120		250*168*120			

The data are general but not limited.

ADD: 919, Jin'ao International Building, Maidian East Road, Haidian District, Beijing 100088, China.

TEL: +86-15601234979 FAX: +86-10-82207122

EMAIL: sales@kh-graphite-carbon.com

WEB: www.kh-graphite-carbon.com