



Kaiheng Graphite Carbon

Graphite Felt/Foil Specifications

Properties	Units	Values		
		Felt	Foil	Foil
Bulk Density	g/cm ³	0.2-1.5	0.2-1.48	0.2-1.5
Fixed Carbon	%	98-99.5	98-99.5	98-99.5
Sulfur	%	0.1-0.15	0.1-0.15	0.05-0.15
Tensile Strength	MPa	>4	>4	>4
Compressibility	%	>40	>40	>40
Recovery	%	>15	>15	>15
Thickness	mm	0.2-6	0.2-0.8	1.0-1.2
Width	mm	1000-1500	1000-1500	1000-1500
Length	m	1-1.5	1-100	1-50

ADD: 919, Jin'ao International Building, Maidian East Road, Haidian District, Beijing 100088, China.

TEL: +86-15601234979

FAX: +86-10-82207122

EMAIL: sales@kh-graphite-carbon.com

WEB: www.kh-graphite-carbon.com